

TROPICAL HARDWOODS CUMARU

GRADE OVERVIEW:-

FAS - (First and Seconds).

Allowing sound defect. Free of sapwood.

PROPERTIES

BOTANICAL NAME

Dipteryx spp. Principally Dipteryx odorata

DENSITY

1070 kg/m³

DISTRIBUTION

Naturally distributed throughout northern South America and Central America, the tree has been widely cultivated in Mexico and the West Indies, particularly in Jamaica. Although the primary aim of cultivation has been vested in the collection of the tonka beans produced by the tree, commercially valuable as a substitute for vanilla for cocoa production and for flavouring snuff and tobacco, the timber is also an excellent

material

DRYING

Considering its density, the wood is relatively easy to dry. It tends to surface check if dried rapidly, but moderate to slow drying rates should reduce this tendency. Thicker sections are at risk from casehardening

DURABILITY

Very Durable

FNVIRONMENTAL

FSC CREDENTIALS

MOISTURE CONTENT

16% - 20% KD, 30% AD

ORIGIN

South & Central America

PHYSICAL/STRUCTURAL

PROPERTIES

Interlocking grain with heartwood distinctive red-brown to dark brown with a speckled appearance due to white deposits in pores

PURCHASING CYCLE

12 month

STORAGE ADVICE

Under Cover

TYPICAL APPLICATIONS

Heavy structural use, Decking, Marine or

freshwater construction

WORKING QUALITIES

Difficult - Cumaru is a heavy, hard, and tough wood which makes it rather difficult to work, but with sharp tools it saws and bores cleanly, and when severely interlocked grain is absent, planes and finishes to a smooth surface. It takes a high polish, but glues

poorly

CUMARU			
Product	Code	Stocked	Environmental Credentials
AD FSC FAS			
1 x 4"	H0006536	Y	FSC
1 x 5"	H0006353	Y	FSC
1 x 6"	H0006181	Y	FSC
1 x 7"	H0006354	Y	FSC
1 x 8"	H0006355	Y	FSC
1.25 x 6"	H0006182	Υ	FSC
1.5 x 4"	H0006334	Υ	FSC
2 x 3"	H0006335	Υ	FSC
2 x 4"	H0006336	Υ	FSC
2 x 6"	H0006634	Υ	FSC
KD FSC FAS			
1 x 5"	H0006450	Υ	FSC
1 x 6"	H0006451	Υ	FSC
1 x 7"	H0006452	Y	FSC
1 x 8"	H0006449	Y	FSC
1.25 x 8"	H0006571	Υ	FSC
2 x 4"	H0006453	Υ	FSC

Additional specifications, sizes, chain of custody and specials are available to order

