

## Emeri (Idigbo, Framire)

### BOTANICAL NAME

**Terminalia ivorensis**



### OVERVIEW

FAS – (First Seconds)

## Further Product Information

### DIMENSIONS

#### **KD FSC FAS (Emeri)**

- 78mm
- 65mm
- 52mm
- 40mm
- 26mm

#### **KD Legal FAS (Emeri)**

- 78mm
- 65mm
- 40mm
- 34mm
- 26mm

#### **KD FAS (Emeri)**

- 52mm
- 40mm
- 34mm
- 26mm

## ENVIRONMENTAL CREDENTIALS

### **Certification**

FSC

3rd party COC

### **Origin**

West & Central Africa

## TECHNICAL INFORMATION

### **Density**

560 kg/m<sup>3</sup> (can vary by up to 20%)

### **Physical Structure**

Emeri has excellent strength properties, comparing well with teak, though weaker in bending and in compression along the grain. It has excellent strength properties, being as strong and stiff as English oak in bending, although considerably softer and less resistant to shock loads. It splits easily and has been used in West Africa for roof shingles

### **Durability**

Moderately durable

### **Drying**

Emeri dries readily and well, with little distortion and splitting, and shrinkage is small

### **Working Qualities**

Medium – The timber works easily with most hand and machine tools. It has little dulling effect on cutting edges and a clean finish is obtained in most operations. There is a tendency however, for the grain to pick up when quarter-sawn material is planed

### **Storage Advice**

Under cover

### **Purchasing Cycle**

12 month