

# American White Ash

## BOTANICAL NAME

**Fraxinus spp**



## OVERVIEW

FAS, FAS/FAS IF, No.1 Common, No.2 Common. Ash can also be purchased with colour selection such as W1F (white 1 face).

## Further Product Information

### APPLICATIONS & USES

Furniture, flooring, doors, architectural interiors, high class joinery and mouldings, kitchen cabinets, panelling, tool handles. A versatile good looking wood offering great value plus wide range of joinery and furniture applications

### DIMENSIONS

#### **KD FAS/FAS1F (Ash American White Kiln Dried)**

- 1"
- 1 x 8"+
- 1 x 13"+
- 1.25"
- 1.25 x 8"+
- 1.25 x 13"+
- 1.5"
- 1.5 x 8"+
- 1.5 x 13"+
- 2"
- 2 x 8"+

- 2 x 13”+
- 2.5”
- 3”
- 4”

**KD FAS/FAS1F FSC (Ash – American White Kiln Dried)**

- 1”
- 1.25”
- 1.5”
- 2”
- 2.5”
- 3”
- 4”

**KD FAS/FAS1F W1F (Ash – American White Kiln Dried)**

- 1”

**KD Prime – RTW (Ripped to width) (Ash – American White Kiln Dried)**

- 1 x 3”
- 1 x 4”
- 1 x 5”
- 1 x 6”
- 1 x 7”

**ENVIRONMENTAL CREDENTIALS**

**Certification**

FSC  
FSC CW

**Origin**

North America

**TECHNICAL INFORMATION**

**Density**

670 kg/m<sup>3</sup> (Density can vary by 20% or more)

**Physical Structure**

Properties Sapwood is light in colour with heartwood varying from light brown to darkish red

**Durability**

Not durable

**Drying**

Dries with little distortion

**Moisture Content**

8 – 10% (+/-2%)

**Working Qualities**

Ash machines well, is good in nailing, screwing and gluing as well as being stained and polished to a very good finish. Good stability means little movement in Performance

**Storage Advice**

Under cover

**Purchasing Cycle**

12 month