

## American Cherry

### BOTANICAL NAME

**Prunus serotina**



### OVERVIEW

Grade Tab:- FAS, FAS/FAS IF, No.1 Common, No.2 Common. Cherry is a species which can require sorting for colour such as 90/50 = 90% 1 face + 2 edges sap free, 50% reverse face sap free.

## Further Product Information

### APPLICATIONS & USES

Furniture and cabinet making, high class joinery, kitchen cabinets, mouldings, panelling, flooring, doors, boat interiors, musical instruments, turning and carving

### DIMENSIONS

#### **KD FAS/FAS1F 90/50 (Cherry – American)**

- 1”
- 1 x 8”
- 1.25”
- 1.5”
- 2”
- 2 x 8”
- 2.5”
- 3”
- 4”

#### **KD FAS/FAS1F FSC 90/50 (Cherry – American)**

- 1”

- 1.25"
- 1.5"
- 2"
- 2 x 9"
- 3"

**KD FAS/FAS1F Steamed (Cherry – American)**

- 2"
- 1.25"
- 1"

**ENVIRONMENTAL CREDENTIALS**

**Certification**

FSC

**Origin**

FSC CW

**Origin**

North America

**TECHNICAL INFORMATION**

**Density**

580 kg/m<sup>3</sup>

**Physical Structure**

Hard with a fine straight close grain, Heartwood varies from reddish brown to rich red, SAP wood white to pinkish

**Durability**

Moderately durable

**Drying**

Relatively quick drying with some tendency to warp

**Moisture Content**

8 – 10% (+/-2%)

**Working Qualities**

Easy to machine, nails and glues well and when sanded, stained or polished produces excellent smooth finish. Dries quickly with moderately large shrinkage but is dimensionally stable after kilning

**Storage Advice**

Under cover

**Purchasing Cycle**

12 month