

Oak - American Red

BOTANICAL NAME

Quercus spp



OVERVIEW

FAS, FAS/FAS IF, No.1 Common, No.2 Common.

Further Product Information

APPLICATIONS & USES

Construction, furniture, flooring, architectural interiors, internal joinery, stairs and mouldings, doors, kitchen cabinets, panelling and coffins

DIMENSIONS

KD FAS/FAS1F (Oak – American Red)

- 1”
- 1.25”
- 1.5”
- 1.5 x 10”+
- 2”
- 2.5”
- 3”

ENVIRONMENTAL CREDENTIALS

Certification

FSC
FSC CW

Origin

North America

Distribution**TECHNICAL INFORMATION****Physical Structure**

Properties Heavy and hard with medium bending range and stiffness and high crushing strength.
Very good for steam bending

Durability

Rated non-resistant to heartwood decay, moderately easy to treat with preservatives

Drying

Dries slowly with a tendency to warp and split, particularly on end grain

Moisture Content

8 – 10% (+/-2%)

Working Qualities

Machines well, nailing and screwing is good although pre-boring is recommended and can be stained and polished to a very good finish. Performs best when dried slowly, reducing opportunity for de-grade such as splits and warp. High shrinkage and susceptible to movement in performance under variable moisture conditions

Storage Advice

Under cover

Purchasing Cycle

12 month