

European Prime Oak

BOTANICAL NAME

Quercus petraea / robur

Further Product Information

APPLICATIONS & USES

Quality Joinery Manufacturing, Joinery, Kitchen Manufacturing, Furniture

DIMENSIONS

Prime S/e European Oak Kiln Dried FSC

- 27mm
- 34mm
- 40mm
- 65mm
- 80mm
- 100mm
- 102mm
- 27mm x 250mm Wider
- 34mm x 250mm Wider
- 40mm x 250mm Wider
- 52mm x 250mm Wider
- 50mm x 50mm

Q/Sawn S/e European Oak Kiln Dried FSC

- 52mm
- 40mm
- 34mm
- 27mm

Prime S/e European Oak Kiln Dried PEFC

- 52mm
- 27mm
- 34mm
- 40mm



- 65mm
- 80mm
- 100mm x 100mm

Prime S/e European Oak Strips K/d PEFC

- 27mm x 100mm
- 27mm x 120mm
- 27mm x 140mm
- 27mm x 150mm
- 27mm x 160mm
- 27mm x 170mm
- 27mm x 180mm
- 27mm x 200mm
- 27mm x 220mm

Prime S/e C4F European Oak Strips K/d

- 27mm x 150mm

S/e European Pippy Oak Kiln Dried

- 27mm

ENVIRONMENTAL CREDENTIALS**Certification**

FSC
PEFC

Origin

France, Germany, Italy, Croatia

TECHNICAL INFORMATION**Density**

700 kg/m³

Physical Structure

Straight Grained Planks 3-4 Face clear Generally Consistent in Colour

Durability

Durable

Moisture Content

13% (Average)

Supplied Finish

Rough Sawn

Storage Advice

Always undercover

Wastage Allowance

40% Recommended