

Small Mouldings - Meranti

BOTANICAL NAME

Shorea spp



OVERVIEW

Select & better. Colour is red to dark brown, planed surfaces fairly lustrous in appearance with surface being course.

No knots, limited pin hole.

Further Product Information

APPLICATIONS & USES

General joinery, furniture, plywood and cladding

DIMENSIONS

Small Mouldings (Meranti)

- 6 x 6mm Quadrant
- 9 x 9mm Quadrant
- 12 x 12mm
- 15 x 15mm
- 18 x 18mm
- 21 x 21mm
- 15 x 15mm Scotia
- 6 x 18mm Half Round
- 6 x 21mm Half Round
- 12 x 15 Wedge Bead

– 23 x 26mm Fire Check Hockey Stick

ENVIRONMENTAL CREDENTIALS

Certification

MTCC or similar accreditation

Origin

12- 14% Kiln Dried

TECHNICAL INFORMATION

Density

710 kg/m³

Physical Structure

It has superior bending, flexibility and crushing strength than that of European Oak, although it is not as hard

Durability

Moderately durable

Moisture Content

12- 14% Kiln Dried

Working Qualities

Works well with a smooth finish when machined, takes a stain or coating well

Supplied Finish

Sawn boards or machined to profile

Storage Advice

Product needs to be kept undercover in dry conditions

Wastage Allowance

25-40%

Stability

Kiln dries well with little distortion, remains stable in the majority of joinery applications