

## Small Mouldings - Meranti

### BOTANICAL NAME

**Shorea spp**



### OVERVIEW

Select & better. Colour is red to dark brown, planed surfaces fairly lustrous in appearance with surface being course.

No knots, limited pin hole.

## Further Product Information

### APPLICATIONS & USES

General joinery, furniture, plywood and cladding

### DIMENSIONS

#### Small Mouldings (Meranti)

- 6 x 6mm Quadrant
- 9 x 9mm Quadrant
- 12 x 12mm
- 15 x 15mm
- 18 x 18mm
- 21 x 21mm
- 15 x 15mm Scotia
- 6 x 18mm Half Round
- 6 x 21mm Half Round
- 12 x 15 Wedge Bead

– 23 x 26mm Fire Check Hockey Stick

## ENVIRONMENTAL CREDENTIALS

### **Certification**

MTCC or similar accreditation

### **Origin**

12- 14% Kiln Dried

## TECHNICAL INFORMATION

### **Density**

710 kg/m<sup>3</sup>

### **Physical Structure**

It has superior bending, flexibility and crushing strength than that of European Oak, although it is not as hard

### **Durability**

Moderately durable

### **Moisture Content**

12- 14% Kiln Dried

### **Working Qualities**

Works well with a smooth finish when machined, takes a stain or coating well

### **Supplied Finish**

Sawn boards or machined to profile

### **Storage Advice**

Product needs to be kept undercover in dry conditions

### **Wastage Allowance**

25-40%

### **Stability**

Kiln dries well with little distortion, remains stable in the majority of joinery applications