

Meranti - PSE

BOTANICAL NAME

Shorea spp



OVERVIEW

Available Grades:-

Select & better. Colour is red to dark brown, planed surfaces fairly lustrous in appearance with surface being course. No knots, limited pin hole.

Further Product Information

APPLICATIONS & USES

General joinery, furniture, plywood and cladding

DIMENSIONS

KD No 1 Common & Better (Wawa)

- 75mm
- 50mm
- 38mm
- 32mm
- 25mm
- 75mm
- 50mm
- 38mm
- 32mm
- 25mm

ENVIRONMENTAL CREDENTIALS

Certification

MTCC or similar accreditation

Origin

South East Asia

TECHNICAL INFORMATION**Physical Structure**

It has superior bending, flexibility and crushing strength than that of European Oak, although it is not as hard

Durability

Moderately durable

Moisture Content

12-14% Kiln Dried

Working Qualities

Works well with a smooth finish when machined, takes a stain or coating well

Storage Advice

Product needs to be kept undercover in dry conditions

Wastage Allowance

25 – 40%

Stability

Kiln dries well with little distortion, remains stable in the majority of joinery applications