

Siberian Larch

BOTANICAL NAME

Larix siberica



OVERVIEW

Available Grades:-

Grade Tab – Unsorted/Sawfalling

Grade Character – Tight intergrown knots up to 40mm diameter are admissible. Sound spike knots no longer than half the width of the board are also acceptable. Resin and bark pockets are allowed up to 2cm² surface area and 2 pieces per board. No insect attack is permissible, although 2 shakes in a width of 1mm in a length of 10% of the board.

Further Product Information

APPLICATIONS & USES

Cladding, decking, flooring, window and door frames

DIMENSIONS

Siberian Larch Cladding

- 25 x 150mm IT1 Shiplap Patt 191
- 25 x 150mm IT2 PTGV Patt IT 19-M2

ENVIRONMENTAL CREDENTIALS

Certification

FSC

Origin

Russia

TECHNICAL INFORMATION**Physical Structure**

Hard, dense timber, colour of heartwood can change from yellowish, brown to pink

Durability

Moderately durable

Moisture Content

Kiln Dried 18 – 20%, green 30% +

Working Qualities

Despite its density and hardness it machines well and takes fixings

Storage Advice

Kiln dried material to be kept under cover, green can be kept outside

Wastage Allowance

10 – 15% length waste

Stability

Minimal movement with boards containing heartwood only