

Thermowood Redwood

BOTANICAL NAME

Pinus sylvestris



OVERVIEW

Available Grades:-

Sawfalling excluding 6ths.

Further Product Information

APPLICATIONS & USES

Cladding, Decking, Saunas

DIMENSIONS

Thermowood Redwood Cladding

- 25 x 125mm IT2 PTGV Patt IT 19-M2
- 25 x 125mm IT1 -Shiplap Patt 191
- 25 x 150mm IT2 -PTGV Patt IT 19-M2
- 25 x 150mm IT1 -Shiplap Patt 191

ENVIRONMENTAL CREDENTIALS

Certification

PEFC

Origin

Finland

TECHNICAL INFORMATION

Physical Structure

Non-structural, small sound knots

Durability

Class 2& Durable

Moisture Content

6 – 8%

Working Qualities

Stable, tangential movement 2 – 3mm

Storage Advice

Under cover

Stability

Care should be taken with storage and machining as product can be brittle, follow Thermowood handbook guidelines Due to stability paint manufacturers are happy to provide 3 year to 10 year warranties subject to conditions Thermowood Redwood can be fire treated, but due to its brittle nature, a 15% wastage factor on end splitting should be calculated

Wastage Allowance

15%