

Louro (Red)

BOTANICAL NAME

Ocotea rubra mez



OVERVIEW

Grade Tab:- FAS – (First and Seconds).

Further Product Information

APPLICATIONS & USES

Joinery – Interior, Furniture, Flooring, Decking, Joinery – Exterior, Cladding

DIMENSIONS

AD FAS (Louro Red)

- 76 x 208mm
- 50 x 205mm
- 50 x 155mm
- 32 x 225mm
- 32 x 200mm
- 32 x 125mm
- 25 x 150mm

ENVIRONMENTAL CREDENTIALS

Certification

FSC

Origin

South & Central America

TECHNICAL INFORMATION

Density

620 – 660 kg/m³

Physical Structure

The wood is somewhat below average in strength properties for tropical hardwoods

Durability

Durable

Drying

The timber is slow to dry and drying requires care to prevent development of distortion and checking. Thick sections tend to remain green in the centre for a considerable time. There is a risk of case hardening if large sections are dried too quickly

Moisture Content

14% – 16% (+/- 2%)

Working Qualities

Easy – The weathering characteristics are very good, there being little loss of surface smoothness, and remarkably little warping or surface checking in unpainted wood exposed to the elements

Storage Advice

Under cover

Purchasing Cycle

12 month