Tatajuba

BOTANICAL NAME

Bagassa guianensis

OVERVIEW

FAS – (First and Seconds).

Further Product Information

APPLICATIONS & USES

Decking, Joinery – Exterior, Marine or freshwater construction

DIMENSIONS

Decking FSC (Tatajuba)
– 28 x 145mm Reversible
– 21 x 145mm Single Grooved

ENVIRONMENTAL CREDENTIALS

Certification
FSC

Origin
South & Central America

TECHNICAL INFORMATION

Density

© International Timber 2026

800 kg/m3

Physical Structure
Tatajuba compares favourably with oak except in shock resistance and shear

Durability
Durable

Drying
Dries slowly but with very little degrade. It has an exceptionally low volumetric shrinkage (10.2 per cent) when drying from the green to oven dry. Tangential shrinkage is 6.6 per cent. and 5.2 per cent radially

Moisture Content
AD 25%

Working Qualities
Good – Easy to work and takes a high lustrous finish, and holds its place well after manufacture. It lends itself well to natural bends for boat building

Storage Advice
Outside

Purchasing Cycle
12 month